

(19) World Intellectual Property  
Organization  
International Bureau



532, 711  
Rec'd PCT/PTO 27 APR 2005



10/532711

(43) International Publication Date  
3 June 2004 (03.06.2004)

PCT

(10) International Publication Number  
WO 2004/045837 A1

(51) International Patent Classification<sup>7</sup>: B29D 30/06,  
30/00

(21) International Application Number:  
PCT/EP2003/012631

(22) International Filing Date:  
12 November 2003 (12.11.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
PCT/IB02/04833  
20 November 2002 (20.11.2002) IB

(71) Applicant (for all designated States except US): PIRELLI  
PNEUMATICI, S.P.A. [IT/IT]; Viale Sarca, 222, I-20126  
Milano (IT).

(72) Inventors; and

(75) Inventors/Applicants (for US only): CANTU' Marco  
[IT/IT]; Via Fornace, 9, I-20040 Carnate (IT). CASALI,  
Andrea [IT/IT]; Via Toselli, 57, I-20091 Bresso (IT).  
MISANI, Pierangelo [IT/IT]; Via Oslavia, 30, I-20052

Monza (IT). PIANTANIDA, Pier, Giuseppe [IT/IT];  
Via Raspagna, 5, I-28047 Oleggio (IT). AZZARETTO,  
Riccardo [IT/IT]; Viale Suzzani, 269, I-20162 Milano  
(IT).

(74) Agents: GIANNESI, Pier, Giovanni et al.; Pirelli & C.  
S.p.A., Viale Sarca, 222, I-20126 Milano (IT).

(81) Designated States (national): AE, AG, AL, AM, AT, AU,  
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,  
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,  
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,  
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,  
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE,  
SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ,  
VC, VN, YU, ZA, ZM, ZW.


(84) Designated States (regional): ARIPO patent (BW, GH,  
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),  
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,  
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE,  
SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA,  
GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

[Continued on next page]

(54) Title: METHOD AND APPARATUS FOR MOLDING AND CURING A TYRE FOR VEHICLE WHEELS



(57) Abstract: A method of molding and curing a tyre for vehicle wheels comprises the steps of: building a green tyre (50) on a toroidal support (10) having an outer surface substantially conforming in shape to the inner surface of said green tyre (50); heating said toroidal support (10) to transmit heat to the inner surface of the tyre in contact with said toroidal support (10); pressing said inner surface of said green tyre (50) against said outer surface of said toroidal support (10) by means of at least one secondary working fluid under pressure; pressing an outer surface of said green tyre (50) against the walls of a molding cavity (104) defined in a vulcanisation mold (102), by means of a primary working fluid under pressure passing in at least one diffusion gap between said outer surface of said toroidal support (10) and said inner surface of said green tyre (50); said primary working fluid under pressure being heated so as to supply heat to said green tyre (50) in order to cause vulcanisation of same.

WO 2004/045837 A1



— before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

METHOD AND APPARATUS FOR MOLDING AND CURING A TYRE FOR  
VEHICLE WHEELS

D e s c r i p t i o n

5

The present invention relates to a method and an apparatus for molding and curing a tyre for vehicle wheels.

- 10 In a tyre production cycle it is provided that following a building process in which the different tyre components are made and/or assembled, a molding and curing process is carried out which aims at defining the tyre structure in accordance with a desired geometry, usually exhibiting  
15 a particular tread pattern.

For the purpose, the tyre is closed in a molding cavity defined internally of a vulcanisation mold and shaped in accordance with the geometric configuration of the outer  
20 surfaces of the tyre to be obtained.

A tyre generally comprises a toroidally ring-shaped carcass including one or more carcass plies, strengthened with reinforcing cords lying in radial planes, i.e.  
25 containing the rotation axis of the tyre. Each carcass ply has its ends integrally associated with at least one annular reinforcing metal structure, usually known as bead core, constituting the reinforcing piece at the beads, i.e. at the radially internal ends of said tyre,  
30 the function of which is to enable assembling of the tyre with a corresponding mounting rim. Placed crownwise to said carcass is a band of elastomer material, called tread band, in which at the end of the curing and vulcanisation steps a raised pattern is formed for ground  
35 contact. A reinforcing structure usually known as belt structure is placed between the carcass and tread band. This structure in the case of tyres for cars usually

- 2 -

comprises at least two radially superposed strips of rubberised fabric provided with reinforcing cords, usually of metal material, disposed parallel to each other in each strip and in crossed relationship with the cords of the adjacent strip, preferably symmetrically disposed with respect to the equatorial plane of the tyre.

Preferably, said belt structure further comprises, at a radially external position thereof, at least on the ends of the underlying strips, a third layer of textile or metallic cords as well, that are disposed circumferentially (at 0 degrees).

Finally, in tyres of the tubeless type i.e. devoid of an air tube, a radially internal layer generally called liner is present which has imperviousness features to ensure the tyre air-tightness.

To the aims of the present invention it is to be pointed out that by the term "elastomer material" it is intended a composition comprising at least one elastomer polymer and at least one reinforcing filler. Preferably, this composition further comprises additives, such as cross-linking and/or plasticizing agents, for example. By virtue of the presence of the cross-linking agents, this material can be cross-linked through heating, so as to form the final manufactured article.

There are molding and curing methods in which a green tyre put on a rigid toroidal support is arranged within the mold. Said methods are preferably employed for tyres that, following recent building processes, are produced starting from a limited number of elementary semifinished products fed onto a toroidal support the outer profile of which is coincident with that of the radially internal surface of the tyre that is wished to be produced. Said

- 3 -

toroidal support is moved, preferably by a robotized system, between a plurality of stations in each of which, through automated sequences, a particular building step of the tyre is carried out (see document EP 0 928 680 in  
5 the name of the same Applicant, for example).

The European Patent Application published under No. 0 976 533 in the name of the same Applicant discloses a method and an apparatus for molding and curing tyres for vehicle  
10 wheels in which the green tyre built on a toroidal support is closed in a vulcanisation mold; subsequently steam or other fluid under pressure is fed into at least one gap for fluid diffusion created between the outer surface of the toroidal support and inner surface of the  
15 tyre.

The Applicant could verify that by a method of the above illustrated type, at the end of the molding and curing step, the obtained tyre may sometimes exhibit some  
20 faults. This mainly takes place because the working fluid (i.e. the vulcanisation fluid) comes directly into contact with the innermost layer of the tyre, since for tyres directly assembled and cured on the same toroidal support there is not the effect of the vulcanisation  
25 bladder. Said bladder when it is present within the green tyre in the vulcanisation mold, allows a uniform distribution of the elastomer material against the mold also correcting small working faults due to junctions, slight manual errors or errors of the building drum, for  
30 example. In fact, it should be remembered that in traditional building processes, i.e. when semifinished products even of great sizes (such as carcass plies, belt strips, tread band, for example) are assembled on cylindrical building drums and the green tyre is shaped  
35 into a toroidal conformation by appropriate devices (mechanical or pneumatic devices, for example) associated with the drums themselves, at the end of the working

- 4 -

operation green tyres are obtained that are disengaged from their building and shaping drum/s and can therefore internally house said vulcanisation bladder.

5 In particular, the Applicant could ascertain during molding and curing of the tyres directly built on a toroidal support that, while the working fluid under pressure is fed between the outer surface of the toroidal support and the inner surface of the green tyre, the  
10 various components of elastomer material still in an uncured state, i.e. in a plastic state, can take an anomalous arrangement with respect to the design specifications. In particular, the carcass ply or plies can move away from their position in the bead region and  
15 slip off due to the expansion to which the tyre is submitted by said working fluid. In this way tensioning of the carcass ply or plies determined by the molding step is lower than it is provided to be for the finished tyre.

20

In the same manner as the carcass ply, other components of the green tyre can slide relative to each other due to the inner vulcanisation pressure during the first minutes of this process, i.e. when the plastic features of the  
25 elastomer material are more present. This phenomenon is more felt in the bead region, where in addition to partial slipping off of the carcass plies, phenomena of lack or accumulation of material are observed that give rise to formation of steps and discontinuities on the  
30 bead itself.

The Applicant has perceived that by at least partly fixing the geometry of the beads and the innermost surface of the tyre, i.e. that tyre portion in contact  
35 with the toroidal support that is the first to come into contact with the working fluid during vulcanisation, the above mentioned drawbacks can be overcome.

- 5 -

In more detail the Applicant has found that by pressing the green tyre from the outside to the inside and simultaneously supplying heat to the inner surface of said tyre, at least partial vulcanisation of the innermost layer of the tyre and of the bead region is obtained, so that a molding and curing step can be subsequently performed without involving lack of homogeneity and irregularities in the finished tyre.

10

In fact the working fluid under molding and curing conditions is in direct contact with parts of the tyre that have already been partly vulcanised and therefore no longer exhibit a plastic behaviour of the material but an almost elastic one. In this case it is obtained a uniform distribution against the mold of the elastomer material belonging to the outermost tyre layers. In addition tension of the carcass ply or plies due to the vulcanisation pressure does not cause any slipping off of the plies at the beads, since the ply or plies have become substantially integral with the elastomer materials present in this region following partial vulcanisation of same.

25

In a first aspect, the invention relates to a method of molding and curing a tyre for vehicle wheels comprising the steps of: building a green tyre on a toroidal support having an outer surface the shape of which substantially matches that of an inner surface of said green tyre; heating said toroidal support to transmit heat to the inner surface of the tyre in contact with said toroidal support; pressing said inner surface of said green tyre against said outer surface of said toroidal support through at least one secondary working fluid under pressure; pressing an outer surface of said green tyre against the walls of a molding cavity defined in a vulcanisation mold, through a primary working fluid under

30

35

- 6 -

pressure passing in at least one diffusion gap between said outer surface of said toroidal support and said inner surface of said green tyre; said primary working fluid under pressure being heated so as to supply heat to  
5 said green tyre to cause vulcanisation thereof.

In a second aspect the invention relates to an apparatus for molding and curing a tyre for vehicle wheels, said apparatus comprising: an airtight vulcanisation mold  
10 arranged to receive a toroidal support adapted to support a green tyre within a molding cavity; at least one passage device adapted to feed at least one primary working fluid under pressure, which is formed through said toroidal support and opens onto the outer surface of  
15 same, so as to enable passage of said primary working fluid under pressure towards the inner surface of said green tyre; a feeding device to supply a secondary working fluid under pressure which is operatively associated with said vulcanisation mold to press said  
20 green tyre from the outside to the inside onto said outer surface of said toroidal support; heating devices to heat said toroidal support; heating devices to heat said primary working fluid to transmit heat to said green tyre and cause vulcanisation of same.

25

In a third aspect, the invention relates to an apparatus for molding and curing a tyre for vehicle wheels, said apparatus comprising: a vulcanisation mold arranged to receive a toroidal support adapted to support a green  
30 tyre within a molding cavity; at least one passage device, adapted to feed at least one primary working fluid under pressure, which is formed through said toroidal support and opens onto the outer surface of same, so as to enable passage of said primary working  
35 fluid under pressure to the inner surface of said green tyre; heating devices to heat said primary working fluid to transmit heat to said green tyre and cause



- 7 -

vulcanisation of same; an airtight container arranged to receive said toroidal support; a feeding device to supply a secondary working fluid under pressure which is operatively associated with said airtight container for pressing said green tyre from the outside to the inside onto said outer surface of said toroidal support; heating devices to heat said toroidal support.

Further features and advantages of the invention will become more apparent from the detailed description of some preferred, but not exclusive, embodiments of a method and an apparatus for molding and curing a tyre for vehicle wheels in accordance with the present invention.

This description will be set out hereinafter with reference to the accompanying drawings, given by way of non-limiting example, in which:

- Fig. 1 is a vertical view partly in section of a preferred embodiment of the apparatus in accordance with the invention during a step of the method in question;
- Fig. 2 is a vertical view partly in section of a preferred embodiment of the apparatus in accordance with the invention during a further step of the method in question;
- Fig. 3 is a vertical view partly in section of a device belonging to an embodiment of the apparatus in accordance with the invention;
- Fig. 3B is a vertical view partly in section of a device belonging to another embodiment of the apparatus in accordance with the invention;
- Fig. 4 is a diagram showing the course of pressure over time in relation to the working fluids employed for carrying out the concerned method.

With reference to Fig. 1, a molding and curing apparatus for vehicle wheel tyres in accordance with a first embodiment of the present invention has been generally

- 8 -

identified by reference numeral 101.

Apparatus 101 comprises a vulcanisation mold 102 operatively associated with an airtight container 103.

5

Preferably, the mold 102 can be made up of a lower half 102A and an upper half 102B, in engagement with a base 103A and a closing portion 103B of container 103, respectively.

10

In the embodiment shown by way of example, each of the lower 102A and upper 102B halves of mold 102 has a cheek, a lower cheek 130A and an upper cheek 130B respectively, and a crown of sectors consisting of a lower sector 131A and an upper sector 131B, respectively.

15

The lower 102A and upper 102B halves are mutually movable between an open position at which they are spaced apart from each other, and a closed position shown in Figs. 1 and 2, at which they are close to each other to form a molding cavity 104 the inner walls of which defined by said cheeks and said sectors reproduce the geometric configuration of the outer surface of a tyre to be obtained at the end of the molding and vulcanisation steps.

25

In more detail, the cheeks are designed to form the outer surfaces of the opposite tyre sidewalls, whereas the sectors are designed to form the so-called tread band of the tyre itself, by creating therein a series of cuts and longitudinal and/or transverse grooves suitably disposed in accordance with a desired "tread pattern".

30

Apparatus 101 further contemplates use of at least one toroidal support 10 of metal or other rigid material, having an outer surface substantially reproducing the shape of the inner surface of the tyre. The toroidal

35

- 9 -

support 10 is conveniently made up of a drum that can be dismantled, i.e. made up of circumferential segments at least some of which are centripetally movable to take the toroidal support to pieces and enable easy removal of same from the tyre when working is over.

Apparatus 101 further comprises at least one duct 110 (Fig. 2) for a primary working fluid under pressure such as steam, nitrogen or other substantially inert gas or a mixture thereof, which fluid is used as better illustrated in the following, for molding and vulcanisation of the tyre.

Also preferably present in apparatus 101 are heating devices for the mold 102 preferably in the form of a plurality of ducts 105 for passage of a heating fluid.

Preferably, apparatus 101 also comprises an airtight device adapted to contain the toroidal support 10 on which a green tyre 50 has been previously built.

As shown in Figs. 1 and 2, said airtight device in a preferred embodiment can be enclosed and integrated into said mold 102, defining an airtight cavity within the same. Preferably in this case said mold 102 comprises a plurality of seals 106 disposed close to vents for escape of the primary working fluid employed for vulcanisation of said tyre, and at least one circumferential seal 107 placed on the opposite surfaces of the two halves 102A and 102B.

Said circumferential seal 107 may consist of an O-ring or preferably a series of superposed metal rings provided between their opposite surfaces, with a sealing element capable of withstanding the pressures and temperatures of the method described in the following.

- 10 -

A feeding device for a secondary working fluid is operatively associated, in this embodiment, with said mold 102. Said device comprises at least one delivery duct 108 and one discharge duct 109 to respectively feed  
5 and evacuate said secondary working fluid under pressure, such as air, nitrogen or other substantially inert gases within said mold 102, to press the inner surface of said green tyre 50 from the outside to the inside, as better described in the following, against the outer surface of  
10 said toroidal support 10.

Alternatively, an airtight device 200 may be provided (Fig. 3) externally of the mold itself. Said device will substantially be of the same outer shape as mold 102  
15 shown in Figs. 1 and 2, but obviously neither cheeks 130A and 130B nor sectors 131A and 131B illustrated above, i.e. those parts intended for tyre molding, will be present therein. More specifically, said device 200 comprises one lower half 202A and one upper half 202B, in  
20 engagement with a base 203A and a closing portion 203B respectively and at least one circumferential seal 207 put on the opposite surfaces of the two halves 202A and 202B. Also provided in said device 200 and in association therewith is a feeding device for a secondary working  
25 fluid comprising at least one delivery duct 208 and one discharge duct 209 to respectively feed and evacuate said secondary working fluid under pressure such as air, nitrogen and other substantially inert gases within said device 200, to press the inner surface of said green tyre  
30 50 from the outside to the inside, as better described in the following, against the outer surface of said toroidal support 10.

Preferably, as shown in Fig. 3B, said device 200 may  
35 comprise at least a heating device 250 (four in Fig. 3B) disposed substantially in the positions occupied by the cheeks 130A and 130B in said mold 102. Advantageously,

- 11 -

said heating devices 250, as it will be better understood in the following, transmit heat to the external surface of the bead regions of the green tyre 50, helping in said partial vulcanisation of said regions.

5

Optionally, said device 200 may provide at least one duct 210 for said primary working fluid under pressure, which fluid is employed, as better described later on, to heat the outer surface of said toroidal support 10.

10

Said devices 250, may be equipped with electric resistors (not shown in the figures), or alternatively may be connected to said duct 210.

15 In addition, when said device 200 is present, an airtight mold as above described in connection with Figs. 1 and 2 is not required in apparatus 101.

Duct 110 (or 210) is operatively associated with at least one passage device, through a connecting duct (not shown) for example, formed along at least one of the centering shanks of said toroidal support 10, to enable diffusion of said primary working fluid under pressure within said toroidal support 10.

25

Said passage device comprises suitable branches formed in the toroidal support 10, through which said primary working fluid reaches a plurality of ducts opening onto the outer surface of the toroidal support itself, conveniently distributed and sized on the circumferential extension thereof. Distribution and sizes will be of such a nature that introduction of raw elastomer material into said toroidal support 10 is prevented.

35 Preferably, a duct 111 adapted to discharge possible condensate is then provided at the lower part of said molding cavity 104.

- 12 -

In accordance with the method of the invention, the green tyre 50 is disposed on the toroidal support 10 before the latter is inserted, together with the tyre, into the airtight vulcanisation mold 102 arranged in an open condition or into said airtight device 200 if it is decoupled from said mold.

In particular, engagement of the tyre on the toroidal support 10 can be conveniently obtained by building the tyre directly on the support itself. In this way the toroidal support 10 is advantageously utilised as a rigid core for deposition of the different components such as liner, carcass plies, reinforcing structures at the beads, belt strips, sidewalls and tread band that concur in tyre formation. More specifically, said tyre components are preferably obtained by deposition on said toroidal support 10 of semifinished products such as, by way of example, strips of elastomer material, strip-like elements of elastomer material internally comprising a plurality of textile or metallic cords, metal cords preferably made of high tensile steel. Further features on the procedure of laying down the tyre components onto the toroidal support 10 are described in the European Patent Application published under No. 0 929 680 in the name of the same Applicant, for example.

Operation of apparatus 101, once said toroidal support 10 carrying the green tyre 50 has been placed into said mold 102 (or said airtight device 200), involves closure of the apparatus itself and starting of the molding and curing operations.

More specifically, by duct 108 (or 208) said secondary fluid under pressure (identified with "b" in Fig. 4) is sent into a cavity included between the outer surface of said green tyre 50 and the inner surface of said mold 102

- 13 -

(or said device 200). Substantially simultaneously, as shown in Fig. 4, by duct 110 (or 210) said primary working fluid under pressure (identified with "a" in Fig. 4) is sent into said toroidal support 10 to a lower pressure than that of said secondary working fluid. The transient has a duration included between 30 seconds and 1 minute; in a steady-state condition and for a duration of 30 seconds to 6 minutes, the pressure differential is lower than 10 bars, preferably of about 1-2 bars. Since the primary working fluid is of lower pressure, it will remain within said toroidal support 10 without escaping through the previously illustrated ducts. In this way during this step the green tyre 50 is pressed from the outside to the inside so that its inner surface preferably comprising the liner is pressed against the outer surface of the toroidal support 10.

Preferably said secondary working fluid is fed at room temperature, at a pressure generally included between 8 and 18 bars, while said primary working fluid, in this step preferably formed of steam, is fed to a pressure lower than 16 bars and a temperature generally included between approximately 170°C and 210°C.

In the example shown in fig. 4, the transient lasts about one minute, pressure of the secondary working fluid in a steady-state condition is about 16 bars and pressure of the primary working fluid is about 14 bars, the differential pressure therefore being about 2 bars.

As above illustrated, in a steady-state condition this step lasts some minutes (about two in the example shown in Fig. 4). During this period of time the primary working fluid heats the toroidal support 10 which transmits heat to the inner surface of the tyre, and consequently to the bead region and preferably the liner. If the airtight device is enclosed and integrated into

- 14 -

said mold 102, during the above step the cheeks 130A and 130B are heated by said heating fluid supplied into said ducts 105. This heat is substantially transmitted to the external surface of the bead region. Moreover if the airtight device 200 is provided externally of the mold 102, the external surface of said bead region may be heated by said devices 250 powered by said resistors or said primary working fluid as hereinabove described. This heating does not fully cure said parts of the tyre but at all events it is sufficient to give the parts themselves features of elasticity. In particular, the carcass ply or plies are well anchored to the beads and the inner tyre surface, preferably the liner, becomes elastic enough to withstand the subsequent pressure of the molding and vulcanisation process illustrated in the following, without tearing.

Termination of this step involves evacuation of the secondary working fluid through the discharge duct 109 (or 209), preferably in a period of time shorter than 2 minutes (1 minute in the example shown).

If mold 102 is airtight, a subsequent step immediately starts for molding and fully curing said tyre (as shown in Figs. 2, 4). Said step begins through raising of said primary-working fluid pressure to a value included between 18 and 35 bars, preferably 26-28 bars, for the purpose of molding and curing the tyre with the desired tensioning on the carcass ply.

In this step the primary working fluid preferably comprises a steam-nitrogen mixture, although it may consist of steam alone or steam admixed with air or other substantially inert gases, or one or more gases such as air, nitrogen and other substantially inert gases.

Pressure generated by said primary working fluid reaches a diffusion gap created between the outer surface of the



- 15 -

toroidal support 10 and the inner surface of the tyre to be cured.

In a preferential embodiment, the diffusion gap is  
5 directly created following a tyre expansion caused by  
effect of the thrust exerted by said primary working  
fluid. In other words, pressing of the tyre against the  
walls of the molding cavity 104 takes place concurrently  
with an expansion imposed to the tyre itself, until  
10 bringing the outer surface thereof to fully adhere to the  
inner walls of the molding cavity 104. Then said pressing  
operation takes place simultaneously with administration  
of heat to produce cross-linking of the elastomer  
material forming the tyre itself and consequent geometric  
15 and structural definition of the latter. Advantageously,  
said primary working fluid determining the desired  
pressure allowing the tyre to be molded, also supplies  
heat necessary for vulcanisation.

20 It will be recognised that in the concerned method,  
during said expansion imposed to the tyre to complete the  
molding and curing operations, the inner surface of same  
(preferably the liner and part of the beads) is in an  
elastic state, as already said, i.e. these tyre parts are  
25 partly cured for the above stated reasons.

In this case the inner tyre surface behaves like a  
vulcanisation bladder in a conventional vulcanisation  
method, wherein an inflatable bladder acts against the  
30 inner surface of a green tyre, manufactured without the  
aid of a toroidal support, for molding it against the  
mold walls and distribute the elastomer material present  
in the different semifinished products in a  
substantially uniform manner.

35

Consequently, in the method of the invention, although in  
the absence of an inflatable bladder, the inner tyre

- 16 -

surface (preferably the liner) that already has good elasticity features, transmits the primary-working fluid pressure to the whole tyre in a substantially uniform manner and behaves like the inflatable bladder of a traditional method. Therefore, thanks to a uniform molding, a vulcanised tyre substantially meeting the nominal design features is obtained.

Should said airtight device 200 be provided separated from said mold 102, at the end of the step of evacuating said secondary working fluid the tyre is extracted from said device in an automated or manual manner and is placed into a mold in which the molding and curing steps go on in a manner substantially identical with the above described one.

It is to be noted that during the tyre-pressing step from the outside to the inside in order to press the inner tyre surface against the outer surface of the toroidal support 10, heating of said inner tyre surface can be carried out by use of said primary working fluid under pressure conveyed through the toroidal support as previously illustrated, or by heating the toroidal support independently of use of said primary working fluid, by means of electric resistors, for example. In the last-mentioned case pressure of the secondary working fluid can also be of few bars (even 2 or 3), provided the differential pressure keeps within the above stated range.

It will be finally recognised that in the method of the invention said step of pressing the inner surface of the green tyre 50 against said outer surface of the toroidal support 10 can take place indifferently before, after or simultaneously with heating of said toroidal support.

- 17 -

C L A I M S

1. A method of molding and curing a tyre for vehicle wheels comprising the steps of: building a green tyre  
5 (50) on a toroidal support (10) having an outer surface the shape of which substantially matches that of an inner surface of said green tyre (50); heating said toroidal support (10) to transmit heat to the inner surface of the tyre in contact with said toroidal support (10); pressing  
10 said inner surface of said green tyre (50) against said outer surface of said toroidal support (10) through at least one secondary working fluid under pressure; pressing an outer surface of said green tyre (50) against the walls of a molding cavity (104) defined in a  
15 vulcanisation mold (102), through a primary working fluid under pressure passing in at least one diffusion gap between said outer surface of said toroidal support (10) and said inner surface of said green tyre (50); said primary working fluid under pressure being heated so as  
20 to supply heat to said green tyre (50) to cause vulcanisation of same.

2. A method as claimed in claim 1, wherein heating of said toroidal support (10) is carried out by means of  
25 electric resistors.

3. A method as claimed in claim 1, wherein heating of said toroidal support (10) is carried out through said primary working fluid conveyed into said toroidal support  
30 (10).

4. A method as claimed in claim 1, wherein during the step of pressing said inner surface of said green tyre (50) against said outer surface of said toroidal support  
35 (10) by said secondary working fluid under pressure, the pressure of said secondary working fluid is greater than the pressure of said primary working fluid.

- 18 -

5. A method as claimed in claim 4, wherein the pressure of said primary working fluid is less than 16 bars.

5 6. A method as claimed in claim 4 wherein the pressure of said secondary working fluid is included between 8 and 18 bars.

10 7. A method as claimed in claim 1, wherein during the step of pressing an outer surface of said green tyre (50) against the walls of said molding cavity (104) by means of said primary working fluid, the pressure of said primary working fluid is included between 18 and 35 bars.

15 8. A method as claimed in claim 1, wherein the temperature of said primary working fluid is included between 170°C and 210°C.

20 9. A method as claimed in claim 1, wherein said primary working fluid comprises steam and nitrogen.

10. A method as claimed in claim 1, wherein said step of pressing said inner surface of said green tyre (50) against said outer surface of said toroidal support (10) comes before said step of heating said toroidal support (10) in order to transmit heat to the inner surface of said tyre in contact with said toroidal support (10).

30 11. A method as claimed in claim 1, wherein said step of pressing said inner surface of said green tyre (50) against said outer surface of said toroidal support (10) comes after said step of heating said toroidal support (10) in order to transmit heat to the inner surface of said tyre in contact with said toroidal support (10).

35 12. A method as claimed in claim 1, wherein said step of pressing said inner surface of said green tyre (50)

- 19 -

against said outer surface of said toroidal support (10) takes place substantially simultaneously with said step of heating said toroidal support (10) in order to transmit heat to the inner surface of said tyre in contact with said toroidal support (10).

13. A method as claimed in claim 1, further comprising the step of transmitting heat to the external surface of the bead region of said green tyre (50).

10

14. An apparatus for molding and curing a tyre for vehicle wheels, said apparatus (101) comprising: an airtight vulcanisation mold (102) arranged to receive a toroidal support (10) adapted to support a green tyre (50) within a molding cavity (104); at least one passage device adapted to feed at least one primary working fluid under pressure, which is formed through said toroidal support (10) and opens onto the outer surface of same, so as to enable passage of said primary working fluid under pressure towards the inner surface of said green tyre (50); a feeding device to supply a secondary working fluid under pressure, which is operatively associated with said vulcanisation mold (102) to press said green tyre (50) from the outside to the inside onto said outer surface of said toroidal support (10); heating devices to heat said toroidal support (10); heating devices to heat said primary working fluid to transmit heat to said green tyre (50) and cause vulcanisation of same.

15. An apparatus as claimed in claim 14, wherein said feeding device of a secondary working fluid under pressure comprises at least one delivery duct (108) and one discharge duct (109).

16. An apparatus as claimed in claim 14, wherein said primary working fluid is designed to heat said toroidal support (10).

- 20 -

17. An apparatus as claimed in claim 14, wherein said heating devices of said toroidal support (10) comprise electric resistors.

5

18. An apparatus as claimed in claim 14, wherein said airtight mold (102) comprises a lower half (102A) and an upper half (102B) in engagement with a base (103A) and a closing portion (103B) respectively, at least one  
10 circumferential seal (107) placed on the opposite surfaces of the two halves (102A, 102B) and a plurality of seals (106) placed close to vents intended for release of said primary working fluid.

15 19. An apparatus for molding and curing a tyre for vehicle wheels, said apparatus (101) comprising: a vulcanisation mold arranged to receive a toroidal support (10) adapted to support a green tyre (50) within a molding cavity; at least one passage device, adapted to  
20 feed at least one primary working fluid under pressure, which is formed through said toroidal support (10) and opens onto the outer surface of same, so as to enable passage of said primary working fluid under pressure to the inner surface of said green tyre (50); heating  
25 devices to heat said primary working fluid to transmit heat to said green tyre (50) and cause vulcanisation of same; an airtight device (200) arranged to receive said toroidal support (10); a feeding device to supply a secondary working fluid under pressure which is  
30 operatively associated with said airtight device (200) for pressing said green tyre (50) from the outside to the inside onto said outer surface of said toroidal support (10); heating devices to heat said toroidal support (10).

35 20. An apparatus as claimed in claim 19, wherein said airtight device (200) comprises a lower half (202A) and an upper half (202B) in engagement with a base (203A) and

- 21 -

a closing portion (203B) respectively, and at least one circumferential seal (207) placed on the opposite surfaces of the two halves (202A, 202B).

5 21. An apparatus as claimed in claim 19, wherein said feeding device of said secondary working fluid under pressure comprises at least one delivery duct (208) and one discharge duct (209) to respectively feed and  
10 evacuate said secondary working fluid within said device (200).

22. An apparatus as claimed in claim 19, wherein said airtight device (200) comprises at least one duct (210) for feeding said primary working fluid.  
15

23. An apparatus as claimed in claim 19, wherein said heating devices of said toroidal support (10) comprise electric resistors.

20 24. An apparatus as claimed in claim 19, wherein said airtight device (200) comprises at least a heating device (250) for transmitting heat to the external surface of said green tyre (50).

25 25. An apparatus as claimed in claim 24, wherein said heating device (250) is powered by electric resistors.

26. An apparatus as claimed in claims 22 and 24, wherein said heating device (250) is powered by said primary  
30 working fluid.

1/5




FIG 1



2/5




FIG 2




FIG 3




FIG 3b




FIG 4

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 03/0531

**A. CLASSIFICATION OF SUBJECT MATTER**  
IPC 7 B29D30/06 B29D30/00

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)  
IPC 7 B29D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 976 533 A (PIRELLI) 2 February 2000 (2000-02-02) cited in the application paragraphs '0001!', '0002! paragraphs '0015! - '0040! abstract; claims 1-23; figures 1-3	1-26
A	EP 0 928 680 A (PIRELLI) 14 July 1999 (1999-07-14) cited in the application abstract; figures 1-13	1-26
A	EP 1 038 657 A (PIRELLI PNEUMATICI) 27 September 2000 (2000-09-27) paragraphs '0001!', '0002! paragraphs '0017! - '0049! abstract; claims 1-29; figures 1-5	1-26
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the International filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*&\* document member of the same patent family

Date of the actual completion of the international search

17 March 2004

Date of mailing of the international search report

24/03/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Brunold, A

## INTERNATIONAL SEARCH REPORT

International Application No.

PCT/EP 03/031

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 822 047 A (CONCEPTION ET DEVELOPPEMENT MICHELIN SA) 4 February 1998 (1998-02-04) column 7, line 55 - column 8, line 10 abstract; figures 2,5,6,9 -----	1-26
A	DE 355 909 C (ERNEST HOPKINSON) 10 July 1922 (1922-07-10) the whole document -----	1-26
A	US 1 798 210 A (LAURSEN LAURITS A) 31 March 1931 (1931-03-31) page 1, line 9 - page 3, line 51 page 4, line 119 - line 129 claims 1-6; figures 1,3,4 -----	1-26

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 01/0631

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0976533	A	02-02-2000	EP 0976533 A2	02-02-2000
			AT 227209 T	15-11-2002
			AT 251029 T	15-10-2003
			BR 9903255 A	22-02-2000
			BR 9903300 A	21-03-2000
			CN 1246404 A	08-03-2000
			CN 1246405 A	08-03-2000
			DE 69903772 D1	12-12-2002
			DE 69903772 T2	17-07-2003
			DE 69911700 D1	06-11-2003
			EP 1358997 A2	05-11-2003
			EP 0976534 A2	02-02-2000
			ES 2187103 T3	16-05-2003
			JP 2000052349 A	22-02-2000
			JP 2000061945 A	29-02-2000
			PT 976533 T	31-03-2003
			TR 9901821 A2	21-02-2000
			TR 9901822 A1	21-02-2000
			US 2002125615 A1	12-09-2002
			US 6409959 B1	25-06-2002
			US 6332999 B1	25-12-2001
EP 0928680	A	14-07-1999	EP 0928680 A1	14-07-1999
			AT 234194 T	15-03-2003
			BR 9805745 A	08-03-2000
			CN 1225869 A	18-08-1999
			DE 69719771 D1	17-04-2003
			DE 69719771 T2	11-12-2003
			ES 2195109 T3	01-12-2003
			JP 11314284 A	16-11-1999
			PT 928680 T	31-07-2003
			RU 2213009 C2	27-09-2003
			TR 9802757 A1	21-07-1999
			TW 407107 B	01-10-2000
			US 2002029841 A1	14-03-2002
EP 1038657	A	27-09-2000	EP 1038657 A1	27-09-2000
			AT 224296 T	15-10-2002
			BR 0001423 A	20-03-2001
			DE 60000463 D1	24-10-2002
			DE 60000463 T2	15-05-2003
			ES 2182745 T3	16-03-2003
			JP 2000296523 A	24-10-2000
			US 6479008 B1	12-11-2002
EP 0822047	A	04-02-1998	AU 720587 B2	08-06-2000
			AU 3240497 A	05-02-1998
			BR 9704211 A	17-02-1999
			CA 2211030 A1	01-02-1998
			CN 1174119 A	25-02-1998
			DE 69716529 D1	28-11-2002
			DE 69716529 T2	05-06-2003
			EP 0822047 A1	04-02-1998
			ES 2184937 T3	16-04-2003
			JP 10076526 A	24-03-1998
			US 6224808 B1	01-05-2001
DE 355909	C	10-07-1922	NONE	

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No.

PCT/EP 01/0631

Patent document  
cited in search report

Publication  
date

Patent family  
member(s)

Publication  
date

US 1798210

A

31-03-1931

NONE